

Mortars

CRETEREP 70

High Quality Repairing Mortar



General Properties:

- **CRETEREP 70** Is repairing mortar specially formulated to make structural repair to any concrete or masonry surface.
- Consists of two components. component (A) is liquid & component (B) is powder.
- Has maximum aggregate size of 1.00 mm.
- Can be applied on verticals, soffits, or inclined surfaces.
- Used for repairing concrete with thickness beginning from 3mm up to 50 mm per one application.
- Has excellent adhesion & high strength.

Uses:

- Repairing concrete for small thickness up to 50 mm.
- Adhesive mortar for fixing tiles & ceramic to cement substrate especially in swimming pools & water tanks. It's not affected with permanent water.
- Repairing water concrete structure before proofing.
- Screeds having small thickness up to 15 mms.
- Hard layer for industrial floors.

Application:

1. Clean substrate & remove all loose aggregates.
2. Mix. Comp. A (liquid) well and pour in a container.
3. Add Comp. B (powder) to comp. A (liquid) and mix well.
4. Damp substrate before application using water.
5. Use the suitable tool for required application .
6. During the first 24 hours, it is better to keep the patch covered or damp to prevent excessive loss of water.
7. Clean tools immediately after application using water.

Technical Data:

Compressive strength, (ASTM C-109)

Time	Compressive Strength
3 days	200 kg/cm ²
7 days	300 kg/cm ²
28 days	350 kg/cm ²

Setting Time of O.P.C.	: (ASTM C-191) 30 min .
Pulloff strength,	: 1.00 N/mm ² (ASTM D 4541-95) .
Binder	: Hydraulic & synthetic resins .
First setting	: 45 min .
Abrasion	: Pyramid sand test from 0.9 - 0.6 mm. under load 15.5Kg, for length 500m abrasion 4.1 mm after 3 days.
Dilution	: Water, if necessary.
Shelf Life	: 12 months in closed containers away from direct sun light, heat and humidity .

- Environment:**
- **CRETEREP 70** is non toxic and suitable for potable water structures.
 - Boots, rubber gloves, dust masks, and safety goggles.
 - Refer to MATERIAL SAFETY DATA SHEETS (MSDS) .

END OF TECHNICAL DATA

For more information please contact our technical department

Head Office : 21 Takseem El Awkaf – EL Sawah Sq. Cairo – Egypt
 Tel : 002 / 02 24535678 - 24535679 Fax : 002 / 02 24538986
 Web site : www.yasmomisr.com E-mail: yasmo@yasmomisr.com