

Mortars

CRETREP 70P
High Quality Repairing Mortar



General Properties:

- **CRETREP 70P** is one component cement base ready mix repairing mortar used for repairing cement substrata.
- Aggregate size up to 1.0 mm.
- One component, just add water.
- Can be applied to the horizontal vertical, inclined surfaces & soffits
- Repair Mortar obtains high bond strength without using bonding agents.

Uses:

- Repairing concrete especially RC structure for thickness up to 50 mm.
- Repairing for cracks in stone or brick walls.
- Repairing water structure concrete prior to proofing.
- High quality adhesive for submerged surfaces under sever conditions, like ceramic tiles in summing pools.

Application:

1. Clean substrate before application & remove all loose particles.
2. Wet Substrate before application.
3. Put suitable water ratio (10.5%) in suitable container.(2.6 liter / kg powder).
4. Add **CRETREP 70P** to the water & mix well, till you get required consistency.
5. Apply **CRETREP 70P** with the suitable tool for the required application.
6. Clean tools immediately after application using water.

Note: Due care to add the powder component to the water not vice versa.

Technical Data:

Compressive Strength	: (ASTM C-109)		water ratio = 10.5 %
	Time	Compressive Strength	
	1 day	200 Kg /cm ²	
	3 days	350 Kg /cm ²	
	7 days	450 Kg /cm ²	
	28 days	500 Kg /cm ²	
Setting Time of O.P.C.	: (ASTM C-191) Pot life 30 minutes		
Pulloff Strength	: (ASTM D 4541-95)		
	Substrate	Concrete surface	Steel surface
Pull off strength		1.6 N/mm ² Failure to substrate	3 N/mm ²
			Glaze surface of ceramic tiles 1.3 N/mm ²
Abrasion	: Pyramid sand test from 0.9 – 0.6mm, under load 15.5 kg, for length 500m. Abrasion = 4.1 mm after 3 days		
Shelf Life	: 12 months in closed container away from direct sunlight, heat and humidity.		

Environment:

- **CRETREP 70 P** is non toxic and suitable for potable water structures.
- Boots, rubber gloves, dust masks, and safety goggles.
- Refer to MATERIAL SAFETY DATA SHEETS (MSDS).

For more information please contact our technical department

Head Office : 21 Takseem El Awkaf – EL Sawah Sq. Cairo – Egypt
 Tel : 002 / 02 24535678 - 24535679 Fax : 002 / 02 24538986
 Web site : www.yasmomiser.com E-mail: yasmo@yasmomiser.com

Mortars

CRETREP 70P
High Quality Repairing Mortar



END OF TECHNICAL DATA

For more information please contact our technical department

Head Office : 21 Takseem El Awkaf – EL Sawah Sq. Cairo – Egypt

Tel : 002 / 02 24535678 - 24535679 Fax : 002 / 02 24538986

Web site : www.yasmomisr.com E-mail: yasmo@yasmomisr.com