

Finishing

GYPCOAT

Modified Gypsum



General Properties:

- **GYPCOAT** is ready mix modified fine gypsum, enables users to achieve a very high standard finishing. When using it as a single final coat over smooth or rough substrata.
- Initial setting time reaches from 50 - 60 minutes that enables the workers to produce high quality finishing.
- Excellent adhesion to substrate.
- Water ratio 40% that provides high strength of **GYPCOAT**.
- Thickness of final finish coat ranges from 2 mm to 10 mm. and can be applied by machine gun.

Substrate:

- All cement substrate.
- All kinds of bricks and stones.

Uses:

- Final plaster one shot for Fair face concrete.
- Interior finishing.
- Repairing to plaster.
- As bonding agent for fiber glass tissue.

Application:

1. Clean substrate well. and wet with water especially in summer.
2. Pour water in a wide vessel then add **GYPCOAT** gradually then mix well manually or by a mechanical mixer
3. Apply **GYPCOAT** using a stainless steel trowel with a thickness not more than 10mm.

Note: The temperature of substrate should not exceed 30°C during application & it is recommended to damp the surface using water, especially in summer.

Technical Data:

Color	: White powder.
Compressive Strength	: 60 kg / cm ²
Thickness	: From 2 mm up to 10 mm.
Coverage	: 1 kg covers 1 m ² for thickness 1 mm.
Environment	: Friendly
Setting Time	: 50-60 minutes
Water Ratio	: About 0.4 liter / kg GYPCOAT
Packaging	: 20 Kg
Shelf Life	: 12 months in closed container and away from sunlight, heat and humidity.

- Environment:**
- Boots, rubber gloves, dust masks, and safety goggles.
 - Refer to MATERIAL SAFETY DATA SHEETS (MSDS)

For more information please contact our technical department

Head Office : 21 Takseem El Awkaf – EL Sawah Sq. Cairo – Egypt
 Tel : 002 / 02 24535678 - 24535679 Fax : 002 / 02 24538986
 Web site : www.yasmomISR.com E-mail: yasmo@yasmomISR.com



28437/A

28437/B

28437/C

Finishing

GYPCOAT
Modified Gypsum



END OF TECHNICAL DATA

For more information please contact our technical department

Head Office : 21 Takseem El Awkaf – EL Sawah Sq. Cairo – Egypt
Tel : 002 / 02 24535678 - 24535679 Fax : 002 / 02 24538986
Web site : www.yasmomISR.com E-mail: yasmo@yasmomISR.com



28437/A

28437/B

28437/C