

Finishing

# GYPCOAT 200

## Modified Gypsum



### General Properties:

- **GYPCOAT 200** is modified ready mix gypsum, combined with selected graded aggregates, to achieve higher thickness without cracks.
- Can be applied with thickness from 5mm up to 50mm
- Excellent adhesion to substrate.
- Can be applied by machine gun.
- Setting time range between 40-60 min.

### Substrate:

- All cement substrate.
- All kinds of brick work.
- All kinds of stones.

### Uses:

- Plaster coat instead of cement render can be applied till thickness 50 mm one shot.

### Application:

1. Clean substrate well.
2. Wet substrate with water especially in summer.
3. Pour water in a wide vessel then add **GYPCOAT 200** gradually to the water.
4. Mix well manually or by a mechanical mixer.
5. Apply **GYPCOAT 200** using a stainless steel trowel with a thickness up to 50 mm.

### Technical Data:

<b>Color</b>	: Off white
<b>Specification</b>	: Complies with BS 1191 part 2.s - ASTM C28
<b>Compressive Strength</b>	: 75 Kg/cm <sup>2</sup>
<b>Thickness</b>	: 5 mm to 50 mm as one coat
<b>Consumption</b>	: 1 ton covers 130-140 m <sup>2</sup> 5mm thickness
<b>Water Ratio</b>	: 0.26 % from <b>Gypcoat 200</b> powder
<b>Environment</b>	: Friendly
<b>Setting Time</b>	: 40 - 60 minutes
<b>Packaging</b>	: 25 Kg
<b>Shelf Life</b>	: 12 months in closed container and away from sunlight, heat and humidity.

- Environment:**
- Boots, rubber gloves, dust masks, and safety goggles.
  - Refer to MATERIAL SAFETY DATA SHEETS (MSDS)

END OF TECHNICAL DATA

### For more information please contact our technical department

Head Office : 21 Takseem El Awkaf – EL Sawah Sq. Cairo – Egypt  
 Tel : 002 / 02 24535678 - 24535679 Fax : 002 / 02 24538986  
 Web site : [www.yasmomISR.com](http://www.yasmomISR.com) E-mail: [yasmo@yasmomISR.com](mailto:yasmo@yasmomISR.com)



28437/A

28437/B

28437/C